

**USE OF HIGH-VOLUME CLASS F FLY ASH
FOR STRUCTURAL GRADE CONCRETE ***

By

Tarun R. Naik, Ph.D., P.E.
Director, Center for By-Products Utilization
Department of Civil Engineering and Mechanics
College of Engineering and Applied Science
University of Wisconsin - Milwaukee
P.O. Box 784
Milwaukee, WI 53211
Phone: (414) 229-6696

Vasanthi Sivasundaram, M.S., P.E.
Research Engineer, CANMET
Department of Energy, Mines and Resource
Ottawa, Canada
Phone: (613) 992-6455

and

Shiw S. Singh, Ph.D., P.E.
Post Doctoral Fellow, Center for By-Products Utilization
College of Engineering and Applied Science
The University of Wisconsin - Milwaukee
P.O. Box 784, Milwaukee, WI 53211
Phone: (414) 229-6696

Naik, Sivasundaram, Singh

ABSTRACT

This research was carried out to investigate performance of structural grade concrete incorporating high volumes of low-calcium fly ash. Two different ASTM Class F fly ashes were used.

A Portland cement concrete, designed to have 28-day compressive strength of 6000 psi (41 MPa), was used in this investigation as a control concrete. Concrete mixes were also designed to have fly ash substitution based on total cement weight in the range of 0 - 60% by weight. Water to cementitious ratio was maintained approximately constant and the desired workability was achieved by using a superplasticizer.

Concrete was tested for compressive strength, splitting tensile strength, and modulus of elasticity in accordance with ASTM test methods. Compressive strength and splitting tensile strength of concrete were determined at ages 1, 7, and 28 days whereas modulus of elasticity was determined at 7 and 28 days.

High replacement of cement by fly ash in concrete caused reduction in compressive strength, splitting tensile strength, and modulus of elasticity within the experimental range. Compressive strength of fly ash concrete was slightly lower than the reference

Naik, Sivasundaram, Singh

concrete up to fly ash addition of 60 percent. However, fly ash concretes achieved adequate strengths appropriate for structural application even at the 60% cement replacements.

INTRODUCTION

Large amounts of fly ash have been used in mass concretes for a long time, with the intention of reducing cost and controlling temperature rise in order to reduce cracking at early ages (1-7).

Most current uses of low-calcium fly ash are in construction of pavements. Since paving concrete contains low-water-to-cementitious materials ratio, workability of the concrete is considerably reduced, resulting in its possible unsuitability for structural applications. In order to improve workability for mixtures with low-water to-cementitious ratio for structural applications, either plasticizers, water-reducing admixtures, or superplasticizers are used. Recently, researchers (13,14) have shown that superplasticized high-volume fly ash concrete can be proportioned to have high-early-strength 1500-3000 psi (10-20 MPa) at 3 days, and high 28-day strength 5000-8700 psi (35-60 MPa), suitable for structural grade concrete.

In the U.S.A., most studies have been primarily concerned

Naik, Sivasundaram, Singh

with utilization of high-volume fly ash in the construction of highways base courses and dams. However, no work has been done in regards to the use of high-volume fly ash in manufacture of high-strength structural grade concretes. This research was primarily undertaken

with a view to developing technologies for large scale utilization of Class F fly ash in production of structural grade concrete.

Naik, Sivasundaram, Singh

PREVIOUS STUDIES

Addition of low-alkali Class F fly ash in concrete generally increases durability of concrete subjected to alkali-silica reaction by reducing reactive alkali content of concrete mixes. Additionally, use of fly ash in concrete reduces its permeability which in turn diminishes alkali aggregate reaction that can occur due to water penetration in the structures (1).

A number of studies have been conducted to develop Class F fly ash mortars and concretes for structural applications (8-17).

Swamy et. al. (8) reported that concrete mixes containing 30 percent by weight of fly ash (ASTM Class F) could be proportioned to have adequate workability and early one-day strength and elastic modulus for structural applications. The dosage of admixtures or superplasticizers were adjusted to obtain cohesiveness and workability with slumps in excess of 4 in. (100 mm) for easy placability in structural members with steel reinforcement. Swamy and Mahmud (9) developed data on mix proportions, strength and modulus of elasticity for structural grade concrete made with 50% low-calcium fly ash (ASTM Class F), and a superplasticizer. Their

results showed that for concretes with low-water-to-cementitious

Naik, Sivasundaram, Singh

materials ratio of 0.32 to 0.42, high-early strength of 1800 to 3000 psi (12 to 20 MPa) in one day and 28-day strengths of 6500 to 8700 psi (45 to 60 MPa) could be produced with slump in excess of 150 mm (6 in). Under moist curing condition, fly ash concretes showed about 50 - 100% higher strength at one year age compared to their strengths at 28-day age.

Recently, extensive research work has been conducted at CANMET concerning utilization of high-volume ASTM Class F fly ash in structural grade concretes (11-16).

Mukerjee et al. (11) incorporated high volumes of fly ash in concrete through the aid of three different superplasticizers. They reported that satisfactory high-strength concrete can be achieved using large quantities of ASTM Class F fly ash. In this study, the mechanical properties of concrete containing 37% low-calcium fly ash were found to be superior to the properties of the reference concrete.

Malhotra and Painter (12) reported an optimum fly ash content in the range of 50 to 60 percent of cement replacement for structural grade concrete with respect to compressive strength. Giaccio and Malhotra (13) determined properties of superplasticized concrete containing high-volume of Class F fly ash made with ASTM

Naik, Sivasundaram, Singh

Type I and III cement. The properties determined were: (1) compressive strength; (2) flexural strength; (3) splitting tensile strength; and, (4) freezing and thawing resistance. Based on data obtained the authors concluded that concrete containing high-volumes of Class F fly ash possessed excellent mechanical properties for use in structural concrete elements, especially for massive sections.

Sivasundaram et. al. (14) proportioned a number of concrete mixtures incorporating high volumes of low-calcium fly ash, superplasticizer, and air-entraining admixture. A block with dimensions of 5x5x5 ft (1.52 x 1.52 x 1.52 m) was manufactured to evaluate temperature rise due to hydration of cementitious materials. The superplasticized high-volume fly ash concrete showed a most encouraging performance at a water-to-cementitious ratio of about 0.32. The concrete produced had high compressive strength at both early and later ages and high modulus of elasticity and a reduced heat of hydration. In order to evaluate field performance of this concrete a concrete block, measuring 29x24x9 ft (8.84 x 7.32 x 2.74 m) was also cast under controlled temperature conditions. Both the small block cast under laboratory condition and the large block did not develop any observable thermal cracks, and their compressive strength and

Naik, Sivasundaram, Singh

modulus of elasticity values were comparable to those obtained for laboratory specimens. In another study, Sivasundaram et. al. (15) showed that

long-term performance of high-volume fly ash concrete was excellent with respect to compressive strength, modulus of elasticity, diffusion of chloride ions in concrete, etc.

Langley et. al. (16) reported that maximum fly ash percentage might range between 55 and 60 percent of total cement content in order to produce structural grade concrete. Their test results revealed that strength properties, modulus of elasticity, drying shrinkage, creep, and freeze-thaw durability of low-cement and high fly ash content concrete compared favorably to normal Portland cement concrete.

Taniguchi et. al. (17) evaluated performance of high-volume fly ash concrete for use in construction of marine structures. They reported that strength characteristics of high-volume fly ash concrete depended strongly upon type and dosages of chemical activators and curing conditions. Their study of high-volume fly ash concrete with NaCl as a chemical activator showed high-initial strength and good increase in strength with age. Of course, use of NaCl as an accelerator can cause accelerated rebar corrosion. Additionally, high-volume fly ash concrete exhibited good resistance against sea water with respect to strength

Naik, Sivasundaram, Singh

characteristics and volume changes.

EXPERIMENTAL PROGRAM

A Portland cement concrete was proportioned to produce the 28-day strength of 6000 psi (41 MPa). In addition, concrete mixes were also proportioned to incorporate fly ash at various percentages of cement replacements ranging between 40 - 60%. Experiments were designed to evaluate performance of fly ash concretes with respect to compressive strength, splitting tensile strength, and secant modulus of elasticity.

MATERIALS

Portland cement (ASTM Type I) obtained from one source was used in this investigation.

Low-calcium fly ashes, ASTM Type F, were obtained from Oak Creek Power Plant in Oak Creek (OCPP), Wisconsin and Valley Power Plant (VPP) in Milwaukee, Wisconsin. These plants use Western bituminous coal obtained from Pennsylvania Mining District 2.

Naik, Sivasundaram, Singh

Chemical composition and physical properties of the fly ashes were determined using appropriate ASTM test methods. Chemical composition and physical properties data are given in Table 1 for Oak Creek Power Plant fly ash and in Table 2 for Valley Power Plant fly ash.

The fine aggregate was natural sand, and was obtained from a local ready-mix concrete producer. Natural gravel was used as a coarse aggregate. The coarse aggregate was also obtained from the same local concrete producer which had maximum size of 3/4 in. (19 mm).

A Melamine based superplasticizer was utilized in this investigation. The dosages of the superplasticizer were varied to achieve the desired workability of fresh concrete while maintaining the same water to cementitious ratio.

MIXTURE PROPORTIONING

The mix proportion for the reference Portland Cement concrete used in this investigation (Mix No. 0-A) is described in Table 3. All concrete mixtures used in this investigation were non-air

Naik, Sivasundaram, Singh

entrained. In addition to the reference Portland cement concrete, fly ash concretes were designed to have various amounts of fly ash in the range of 40 - 60% by weight based on total cement used.

Concrete mixtures using Oak Creek Power Plant (OCP) Class F fly ash were proportioned to contain fly ash at cement replacement

of 40, 50, and 60 % by weight. The corresponding mixtures were designated as OCP-A, OCP-B, and OCP-D. Water to cementitious materials ratio, $\text{Water}/(\text{Cement} + \text{Fly Ash})$, was maintained at about 0.32. Details of the mixture proportions are given in Table 3.

Concrete mixtures containing Valley Power Plant (VPP) Class F fly ash were proportioned to incorporate fly ash at cement replacement of 50 and 60% by weight. The corresponding mixtures were designated as VPP-E and VPP-K. Water to cementitious materials ratio was kept at approximately 0.32 for Mix No. O-A and VPP-E, and about 0.44 for Mix No. VPP-K. The details of the mix proportions are given in Table 4. Mix No. O-A is the same for both sources of fly ashes.

All the concrete ingredients were kept at room temperature prior to mixing the materials. A rotary drum laboratory mixer was used to prepare concrete mixes. The properties of fresh concretes

Naik, Sivasundaram, Singh

made with ASTM Class F fly ash obtained from OCPP are given in Table 3. The properties of concrete containing ASTM Class F fly ash derived from VPP are presented in Table 4.

6x12 in. (152 x 305 mm) cylindrical specimens were cast in molds for compressive strength, tensile strength, and secant modulus of elasticity measurements for all the concrete mixtures.

The casting and curing of concrete test specimens under laboratory conditions were carried out according to the appropriate ASTM standard methods.

TESTING OF SPECIMENS

Specimens were tested for compressive strength, tensile strength, and secant modulus of elasticity in accordance with the applicable ASTM test methods. Three cylinders were tested for each experimental condition.

Naik, Sivasundaram, Singh

RESULTS AND DISCUSSION

Compressive Strength

Compressive strength data for the concretes containing Class F fly ash obtained from Oak Creek Power Plant (OCP) fly ash is reported in Table 5. Compressive strength versus age relationship is shown in Figure 1. Relation between compressive strength and percentage of OCP fly ash is shown in Figure 2. Compressive strength was found to increase with age for all the fly ash concretes (Figure 1). In general, addition of high volumes of OCP fly ash in concrete caused a reduction in compressive strength (Figure 2) with

respect to concrete containing 611 lb./cu.yd. of Portland cement. Compressive strength at 28-day decreased from 6820 psi (47 MPa) to 5016 psi (35 MPa) when fly ash inclusion was increased from up to 60% of the cement used by weight. The fly ash concrete incorporating 60% fly ash showed compressive strengths of 3200 psi (22 MPa) at the 7-day age and 5000 psi (35 MPa) at the 28-day age. This is considered to be substantial for a concrete containing only 244 lb./cu.yd. (145 kg/m³) of Portland cement. Thus, these results indicate that concrete containing up to 60% of low-calcium fly ash can be proportioned to meet the requirements of strength and workability for structural grade concretes. The desired strength can be achieved by adjusting the amount of fly ash, and

Naik, Sivasundaram, Singh

for the same water to cementitious ratio desired workability can be obtained through the use of superplasticizer. Moisture corrections for aggregates must also be made when aggregates contain greater amount of water than that at the saturated surface dry condition.

The compressive strength data for concrete made with Class F fly ash obtained from the Valley Power Plant (VPP) is shown in Table 6. The compressive strength versus age curves are shown in Figure 3. The relationship between compressive strength and percentage of fly ash inclusion is shown in Figure 4. The compressive strength data obtained with VPP fly ash showed the same general trend as described above for the structural concrete made with OCPP fly ash. However, due to variations between the source

of fly ash, in their physical properties, especially in fineness and pozzolanic activity index, their reactivities varied which caused differences in their measured performance in concrete. The concretes containing VPP fly ash produced sufficiently high compressive strength at all the ages tested up to 50% cement replacement. At 50 percent fly addition, concrete gained strength of about 3000 psi (21 MPa) at 1-day age, which is high enough to meet requirements of early strength gain for most structural

Naik, Sivasundaram, Singh

applications. The concrete also developed sufficient 28-day strength suitable for structural applications even at 60% fly ash inclusion.

Figures 2 and 4 also show that at high fly ash replacement levels, the proportion of fly ash concrete strength to reference concrete strength increased substantially from one day to 28 days.

The high-strength obtained through the use of superplasticizers is attributed to the lower water to cementitious materials ratio for a given consistency and due to the densified concrete mixture. Previous microscopic studies have confirmed that addition of superplasticizers in concrete mixes produces excellent dispersion of cement particles which in turn accelerate the rate of hydration reaction. Consequently, as observed in this project, superplasticized concretes showed higher compressive strength due to low water cement ratio.

Since early age strength for high-volume fly is lower compared to reference concrete longer periods of time will be required to reach the desired strength for stripping formwork. In cases where additional curing time cannot be allowed, the mixture proportion can be adjusted to meet the job requirements in order to reach sufficient strength for stripping within a given length

Naik, Sivasundaram, Singh

of time. It should be pointed out, however, that except for the Mix No. VPP-K, all concretes developed sufficient strength in one day to allow for the form shipping to continue without delay.

Splitting Tensile Strength

Splitting tensile strength data obtained from various concrete mixes is reported in Tables 5 for concrete made with OCPP fly ash and in Table 6 for concrete made with VPP fly ash.

In general, splitting tensile strength increased with age for concretes made with both OCPP and VPP fly ashes (Tables 5 and 6).

Also, in general, the tensile strength decreased with an increase in fly ash content in the concrete. However, percent decrease in tensile strength became lower at later ages.

The relationship between tensile strength and age for the concrete made with the fly ash from OCPP is shown in Figure 5.

The

effect of fly ash addition on tensile strength of concrete is presented in Figure 6. Analysis of the results showed that the concrete containing 50% Class F fly ash obtained from Oak Creek Power Plant had 81% of the 28-day tensile strength of the reference concrete. A further decrease in value of the tensile

Naik, Sivasundaram, Singh

strength was obtained when addition of fly ash was further increased to 60%.

The tensile strength versus age data for the concrete containing Class F fly ash from the Valley Power Plant is shown in Figure 7. The relationship between tensile strength and fly ash inclusion is presented in Figure 8. This concrete achieved 73% of the tensile strength of the referenced concrete at fly ash addition of 50% and the age of 28 days (Figure 8). When fly ash addition was increased to 60%, the fly ash concrete attained only 45% of the tensile strength of reference concrete.

Modulus of Elasticity

The secant modulus of elasticity data is shown in Tables 5 and 6 for the concretes made with Oak Creek Power Plant fly ash and Valley Power Plant fly ash. In general, modulus of elasticity values increased with increased age, and decreased with an increase in fly ash content, all within a narrow range of possible testing/measuring errors.

The data presented in Tables 5 and 6 indicate that secant modulus values of the concretes made with both of these ASTM Class

Naik, Sivasundaram, Singh

F fly ashes up to 60% fly ash inclusion are sufficient for structural applications. The modulus of elasticity was also computed using ACI Code 318 Eqn' $E_c = W_c^{1.5} \times 33f_c^{1/2}$, where E_c = the static modulus of elasticity, psi; W_c = unit weight, lb/ft³; and f_c = the 28-day compressive strength of standard cylinder. The values computed by the ACI Code equation is presented in Tables 5 and 6 for concretes containing OCPP and VPP fly ashes, respectively. The values of modulus of elasticity computed by the ACI 318 Code equation were within a few percentage points of the actual values.

SUMMARY AND CONCLUSIONS

This study was primarily directed toward evaluation of performance of concrete incorporating high-volume of ASTM Class F fly ash. A Portland cement concrete, designed to have 6,000 psi (41 MPa), was used as a reference concrete. Concrete mixes, containing two different types of low-calcium fly ashes were proportioned to have cement replacements between 40 and 60%. The water to cementitious materials ratio was maintained at approximately 0.32, and the desired workability of concrete mixes were obtained with the aid of a superplasticizer.

In general, both compressive strength and tensile splitting

Naik, Sivasundaram, Singh

strength increased with age, and decreased with increasing fly ash inclusions in the tested range of variables. However, the concrete containing fly ash up to 60% developed compressive strength in excess of 4350 psi (30 MPa) at the 28-day age. At an early 7-day age, the concrete had high early secant modulus of elasticity suitable for use in structural concrete.

Based upon data recorded, it was concluded that superplasticized concrete containing fly ash up to 60% can be proportioned to meet the strength and workability requirement for structural grade concretes.

The chemical, physical and mineralogical properties of fly ash can have appreciable effects on performance of fly ash in concrete. Properties of cement would also influence the performance of concrete. Therefore, it is necessary to determine the optimum mixture proportions for each cement and fly ash source before use.

Naik, Sivasundaram, Singh

REFERENCES

- (1) P.K. Mehta. Concrete Structure, Properties and Materials, Prentice-Hall, Inc., Englewood Cliff, New Jersey, USA.
- (2) P.R. Stodola. Performance of Fly Ash in Hardened Concrete, ACI Concrete International, December 1983, pp. 64-65.
- (3) R.E. Davis, R.W. Carleson, and H.E. Davis. Properties of Cement and Concrete Containing Fly Ash, ACI Journal, Vol. 33, 1937, pp. 577-612.
- (4) B. Mather. Use of Concrete of Low-Portland Cement in Combination with Pozzolans and Other Admixtures in Construction of Concrete Dams, ACI Journal, December 1974, pp. 589-599.
- (5) M.N. Hague, B.M. Langan, and M.A. Ward. High Fly Ash Concretes, ACI Journal, Proc. Vol. 81, No. 1, Jan.-Feb. 1984, pp. 54-60.
- (6) V.H. Dodson. High Percentage Use of Fly Ash in Concrete, in Fly Ash Concrete, Denver Fly Ash Concrete, Inc. and Los Angeles Fly Ash Symposium, Inc., 1983, pp. 801-01 - 802-21.

Naik, Sivasundaram, Singh

- (7) E.E. Berry and V.M. Malhotra. Fly Ash in Concrete, in Supplementary Cementing Materials for Concrete, V.M. Malhotra, Ed., Minister of Supplies and Services, Canada, 1987, pp. 36-163.
- (8) R.N. Swamy, A.R.A. Sami, and D.D. Theodorakopoulos. Early Strength of Fly Ash Concrete for Structural Applications, ACI Journal, September-October, 1983, pp. 414-423.
- (9) R.N. Swamy and H.B. Mahmud. Shrinkage and Creep Behavior of High Fly Ash Content Concrete, in Fly Ash Silica Fume, Slag and Natural Pozzolan in Concrete, V.M. Malhotra, Ed., Proceedings of the Third International Conference, Trondheim, Norway, Vol. 1, ACI SP-114, ACI, Detroit, 1989, pp. 453-475.
- (10) R.N. Swamy and H.B. Mahmud. Mix Proportions and Strength Characteristics of Concrete Containing 50% Low-Calcium Fly Ash, CANMET/ACI, In Fly Ash, Silica Fume, Slag and Natural Pozzolans in Concretes, Proceedings of the Second International Conference, Madrid Spain, Vol. 1, ACI Publication SP-91, April 1986, pp. 413-432.

Naik, Sivasundaram, Singh

- (11) P.K. Mukherjee, M.T. Loughborough, and V.M. Malhotra. Development of High-Strength Concrete Incorporating Large Percentages of Fly Ash and Superplasticizers, ASTM Cement, Concrete and Aggregates, Vol. 4, No. 2, Winter 1983, pp. 81-86.
- (12) V.M. Malhotra and K.E. Painter. Early-Age Strength Properties, and Freezing and Thawing Resistance of Concrete Incorporating High-Volumes of ASTM Class F Fly Ash, the International Journal of Cement Composites and Lightweight Concrete, Vol. 11, No. 2, February 1988.
- (13) G.M. Giaccio and V.M. Malhotra. Concrete Incorporating High-Volumes of ASTM Class F Fly Ash, ASTM Cement, Concrete and Aggregates, Winter 1988, pp. 88-95.
- (14) V. Sivasundaram, G.G. Carette and V.M. Malhotra. Superplasticized High-Volume Fly Ash System to Reduce Temperature Rise in Mass Concrete, Proceedings of the Eighth International Coal Ash Utilization Symposium, Volume 2, Electric Power Research Institute, Washington, D.C., October 1987.

Naik, Sivasundaram, Singh

- (15)V. Sivasundaram, G.G. Carette, and V.M. Malhotra. Long-Term Strength Development of High-Volume Fly Ash Concrete, Presented at the Third International Conference on the Use of Fly Ash, Silica Fume, Slag and Natural Pozzolans in Concrete, Trondheim, Norway, June 1989.
- (16)W.S. Langley, G.G. Carette, and V.M. Malhotra. Structural Concrete Incorporating High Volumes of ASTM Class F Fly Ash, ACI Materials Journal, Vol. 86, No. 5, September-October 1989, pp. 507-514.
- (17)K. Taniguchi, T. Suzuki, Y. Shimomura, H. Ohga, and S. Nagataki. Applicability of High-Volume Fly Ash Concrete to Marine Structures, Third CANMET/ACI International Conference on Fly Ash, Silica Fume, Slag, and Natural Pozzolans in Concrete, Supplementary Papers, compiled by M. Alasali, Trondheim, Norway, 1989, pp. 66-81.

Naik, Sivasundaram, Singh

Table 1: Chemical and Physical Test Data for the Class F Fly Ash
from Oak Creek Power Plant

Chemical Composition	Average, percent	ASTM-C-618
Silicon Oxide, SiO ₂	49.6	-
Aluminum Oxide, Al ₂ O ₃	24.0	-
Iron Oxide, Fe ₂ O ₃	14.4	-
Total, SiO ₂ +Al ₂ O ₃ +Fe ₂ O ₃	88.0	70.0 Min.
Sulfur Trioxide, SO ₃	0.88	5.0 Max.
Calcium Oxide, CaO	3.23	-
Magnesium Oxide, MgO	0.98	5.0 Max.
Potassium Oxide, K ₂ O	2.46	-
Moisture Content	0.11	3.0 Max.
Loss on Ignition	3.5	6.0 Max.

Physical Tests		ASTM C-618
Fineness, % Retained on #325 Sieve	25.7	34 Max.
Pozzolanic Activity Index with Portland Cement, 28 days, % with lime, 7 days, psi	93 1110	75 Min. 800 Min.
Water Requirement, % of Control	103	105 Max.
Soundness, Autoclave Expansion, %	0.08	0.8 Max.
Specific Gravity	2.30	-

Note: 1 psi = 0.0069 MPa

Naik, Sivasundaram, Singh

Table 2: Chemical and Physical Test Data for the Class F Fly Ash
from Valley Power Plant

Chemical Composition	Average, percent	ASTM-C-618
Silicon Oxide, SiO ₂	50.1	-
Aluminum Oxide, Al ₂ O ₃	25.3	-
Iron Oxide, Fe ₂ O ₃	14.7	-
Total, SiO ₂ +Al ₂ O ₃ +Fe ₂ O ₃	90.1	70.0 Min.
Sulfur Trioxide, SO ₃	0.25	5.0 Max.
Calcium Oxide, CaO	1.18	-
Magnesium Oxide, MgO	0.71	5.0 Max.
Potassium Oxide, K ₂ O	2.24	-
Moisture Content	0.11	3.0 Max.
Loss on Ignition	3.5	6.0 Max.

Physical Tests		ASTM C-618
Fineness, % Retained on #325 Sieve	25	34 Max.
Pozzolanic Activity Index with Portland Cement, 28 days, %	88	75 Min.
with lime, 7 days, psi	640	800 Min.
Water Requirement, % of Control	106	105 Max.
Soundness, Autoclave Expansion, %	0.07	0.8 Max.
Specific Gravity	2.32	-

Note: 1 psi = 0.0069 MPa

Naik, Sivasundaram, Singh

Table 3: Concrete Mix Using Oak Creek Power Plant Class F Fly Ash
- 6000 psi (41 MPa) Specified Strength

Mix No.	0-A	OCPA-A	OCPA-B	OCPA-D
Specified Design Strength, psi	6000	6000	6000	6000
Cement, lbs./cu. yd.	611	355	305	244
Fly Ash, lbs./cu. yd.	0	244	305	366
Water, lbs./cu.yd.	195	195	195	195
Water to Cementitious Ratio	0.32	0.33	0.32	0.32
Sand, SSD, lbs./cu. yd.	1544	1499	1487	1476
3/4" aggregates, SSD, lbs./cu. yd.	1887	1831	1818	1804
Slump, inches	2-1/4	4	3	5-1/2
Air Temperature, degrees F	65	65	66	68
Concrete Temperature, degrees F	65	65	66	68
Concrete Density, pcf	158.4	155.2	153.6	152.8
Superplasticizer liters/cu. yd.	4.9	4.7	4.6	4.5

Note: 1 psi = 0.0069 MPa; 1 inch = 25.4 mm
 1 degree C = (degree F - 32)/1.8
 1 lb/cu yd = 0.593 kg/m³; 1 pcf = 16.02 kg/m³
 1 liter = 29.57 x 10³ oz.

Naik, Sivasundaram, Singh

Table 4: Concrete Mix Using Valley Power Plant Class F Fly Ash -
6000 psi (41 MPa) Specified Strength

Mix No.	0-A	VPP-E	VPP-K
Specified Design Strength, psi	6000	6000	6000
Cement, lbs./cu. yd.	611	305	244
Fly Ash, lbs./cu. yd.	0	305	367
Water, lbs./cu.yd.	195	195	266
Water to Cementitious Ratio	0.32	0.32	0.44
Sand, SSD, lbs./cu. yd.	1554	1501	1488
3/4" aggregates, SSD, lbs./cu. yd.	1887	1836	1870
Slump, inches	2-1/4	1-1/2	9-1/2
Air Temperature, degrees F	65	60	65
Concrete Temperature, degrees F	65	60	65
Concrete Density, pcf	158.4	151.6	155
Superplasticizer liters/cu. yd.	4.9	4.5	5.1

Note: 1 psi = 0.0069 MPa; 1 inch = 25.4 mm
 1 degree C = (degree F - 32)/1.8
 1 lb/cu yd = 0.593 kg/m³; 1 pcf = 16.02 kg/m³
 1 liter = 29.57 x 10³ oz.

Naik, Sivasundaram, Singh

Table 5: Concrete Strength Data* Using Oak Creek Power Plant Class F Fly Ash - 6000 psi (41 MPa) Specified Strength

Mix No.	0-A	OCPP-A	OCPP-B	OCPP-D
Specified Strength, psi	6000	6000	6000	6000
Percent Fly Ash	0	40	50	60

Test Age, Days	Compressive Strength, psi			
1	4525	2404	1712	2346
7	6572	4604	4097	3189
28	6820	6343	5140	5016

Test Age, Days	Splitting Tensile Strength, psi			
1	365	251	158	145
7	464	362	360	236
28	541	453	439	353

Test Age, Days	Modulus of Elasticity, psi x10 ⁺⁶			
7	4.92	3.78	-	3.27
28	5.45	4.75	-	4.77
28**	5.43	5.08	4.5	4.73

Note: 1 psi = 0.0069 MPa

*Average of three test specimens.

**Computed by ACI 318 Equation

Naik, Sivasundaram, Singh

Table 6: Concrete Strength Data* Using Valley Power Plant Class F
Fly Ash - 6000 psi (41 MPa) Specified Strength

Mix No.	0-A	VPP-E	VPP-K
Specified Strength, psi	6000	6000	6000
Percent Fly Ash	0	50	60

Test Age, Days	Compressive Strength, psi		
1	4525	3006	553
7	6572	3805	2258
28	6820	5906	4569

Test Age, Days	Splitting Tensile Strength, psi		
1	365	156	45
7	464	271	212
28	541	393	245

Test Age, Days	Modulus of Elasticity, psi x10 ⁺⁶		
7	4.92	3.33	4.07
28	5.45	4.33	-
28**	5.43	4.73	4.30

Note: 1 psi = 0.0069 MPa

*Average of three test specimens.

**Computed by ACI 318 Equation.

List of Tables

Table 1: Chemical and Physical Test Data for the Class F Fly Ash from Oak Creek Power Plant

Table 2: Chemical and Physical Test Data for the Class F Fly Ash from Valley Power Plant

Table 3: Concrete Mix Using Oak Creek Power Plant Class F Fly Ash - 6000 psi (41 MPa) Specified Strength

Table 4: Concrete Mix Using Valley Power Plant Class F Fly Ash - 6000 psi (41 MPa) Specified Strength

Table 5: Concrete Strength Data Using Oak Creek Power Plant Class F Fly Ash - 6000 psi (41 MPa) Specified Strength

Table 6: Concrete Strength Data Using Valley Power Plant Class F Fly Ash - 6000 psi (41 MPa) Specified Strength

Naik, Sivasundaram, Singh

List of Figures

Figure 1: Compressive Strength vs. Age for OCPP Class F Fly Ash

Figure 2: Compressive Strength vs. Percentage Fly Ash for OCPP
Class F Fly Ash

Figure 3: Compressive Strength vs. Age for VPP Class F Fly Ash

Figure 4: Compressive Strength vs. Percentage Fly Ash for VPP
Class F Fly Ash

Figure 5: Tensile Strength vs. Age for OCPP Class F Fly Ash

Figure 6: Tensile Strength vs. Percentage Fly Ash for OCPP Class
F Fly Ash

Figure 7: Tensile Strength vs. Age for VPP Class F Fly Ash

Naik, Sivasundaram, Singh

Figure 8: Tensile Strength vs. Percentage Fly Ash for VPP Class F
Fly Ash